

### Technisches Datenblatt

# Glastic® Glasrod HIR



#### Typische Eigenschaften

- Extremely strong, excellent retention of properties at elevated temperature, easily fabricated
- Cost-Effective
- Dimensionally Stable

#### Typische Industrien

- Generatoren und Motoren
- Trockentransformatoren
- Elektroindustrie
- Elektrische Isolierbauteile
- Schaltanlagen
- Transformatoren

	Testverfahren	Einheit	Wert
<b>Allgemeine Eigenschaften</b>			
Standard Color			Light Green
<b>Mechanische Eigenschaften</b>			
Flexural Strength	ASTM D 790	psi	100,000
Tensile Strength	ASTM D 638	psi	90,000
Tensile Modulus	ASTM D 638	psi X 10 <sup>6</sup>	3
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	60
In-Plane Shear Strength	ASTM D 3914	psi	3,500
Compressive Strength - Axial	ASTM D 695	psi	60,000
Compressive Strength - Transverse	ASTM D 695	psi	16,000
<b>Thermische Eigenschaften</b>			
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10 <sup>-5</sup>	0.6
Wärmeleitfähigkeit	ASTM C 177		2
<b>Physikalische Eigenschaften</b>			
Specific Gravity	ASTM D 792		1.9
Water Absorption	ASTM D 570	%	0.1
<b>Dielektrische Eigenschaften</b>			
Arc Resistance	ASTM D 495	sec.	150
Permittivity, 60 Hz	ASTM D 150		5
Insulation Resistance	ASTM D 257	Ω x 10 <sup>12</sup>	100



	Testverfahren	Einheit	Wert
Electrical Strength - Axial in Oil		kV	80

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc. See correlating profile page for sizing and related information.



#### Röchling Industrial Cleveland, LP

4321 Glenridge Road • 44121 Cleveland/United States (US) • Tel. +1 216 486-0100  
info@glastic.com • www.roechling.com/cleveland

Print: 27/07/2024 • Release: 24/10/2023 • Version: 4.0  
PIM-Version: 51 • PIM-ID: 715314 • PIM-Code: 51-23-6.5.7-4.6.11.7.7.5-8

