

## Technisches Datenblatt

# Glastic® TSF 1312



### Typische Eigenschaften

- UL® Recognized
- NEMA GPO-1
- Cost-Effective

### Typische Industrien

- Generatoren und Motoren
- Trockentransformatoren
- Elektroindustrie
- Elektrische Isolierbauteile
- Schaltanlagen
- Elektronik

	Testverfahren	Einheit	Wert
<b>Allgemeine Eigenschaften</b>			
Part Number			1312
NEMA Grade LI 1-1989	NEMA LI-1		GPO-1/GPO-1P
Standard Color			Brown
UL Temperature Index - Electrical	UL 746B	°C	130
UL Temperature Index - Mechanical	UL 746B	°C	130
UL Recognition File Number			E23525
<b>Mechanische Eigenschaften</b>			
Flexural Strength	ASTM D 790	psi	22,300
Flexural Strength @130°C	ASTM D 790	psi	15,400
Compressive Strength	ASTM D 695	psi	38,900
Tensile Strength	ASTM D 638	psi	9,400
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	8.0
Shear Strength	ASTM D 732	psi	13,400
<b>Thermische Eigenschaften</b>			
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10-5	2.2
Wärmeleitfähigkeit	ASTM C 177		1.8
<b>Flamm Eigenschaften</b>			
UL Subject 94	UL 94		HB
Oxygen Index	ASTM D 2863	%O <sub>2</sub>	21.8



	Testverfahren	Einheit	Wert
<b>Physikalische Eigenschaften</b>			
Water Absorption	ASTM D 570	% by wt.	0.3
Specific Gravity	ASTM D 792		1.78
<b>Dielektrische Eigenschaften</b>			
Electrical Strength - Perpendicular S/T in Air	ASTM D 149	Vpm	417
Electrical Strength - Perpendicular S/T in Oil	ASTM D 149	Vpm	493
Electrical Strength - Parallel S/S in Oil	ASTM D 149	kV	44
Arc Resistance	ASTM D 495	sec.	127
Permittivity, 60 Hz	ASTM D 150		4.2
Dissipation Factor, 60 Hz	ASTM D 150		0.0095
Dissipation Factor, MHz	ASTM D 150		0.01
Permittivity, MHz	ASTM D 150		4.2
Insulation Resistance	ASTM D 257	$\Omega \times 10^{12}$	2.4

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

### Röchling Industrial Cleveland, LP

4321 Glenridge Road • 44121 Cleveland/United States (US) • Tel. +1 216 486-0100  
[info@glastic.com](mailto:info@glastic.com) • [www.roechling.com/cleveland](http://www.roechling.com/cleveland)

Print: 27/07/2024 • Release: 24/10/2023 • Version: 6.0  
 PIM-Version: 58 • PIM-ID: 715321 • PIM-Code: 58-23-6.9.5-4.6.11.7.7.8-6

