

Technisches Datenblatt

Glastic® UTR Composite Tubing

Typische Eigenschaften

- 1,000 Minutes Track Resistance, Electrically Insulating, Highly Flame Resistant, Low Smoke & Smoke Toxicity, UL® Recognized, and Halogen-Free
- Cost-Effective
- Dimensionally Stable

Typische Industrien

- Generatoren und Motoren
- Trockentransformatoren
- Elektroindustrie
- Elektrische Isolierbauteile
- Schaltanlagen
- Elektronik

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
NEMA Grade LI 1-1989	NEMA LI-1		GPO-3
UL Temperature Index - Electrical	UL 746B	°C	130
UL Temperature Index - Mechanical	UL 746B	°C	160
Mechanische Eigenschaften			
Tensile Strength	ASTM D 638	psi	30,700
Tensile Modulus	ASTM D 638	psi X 10 ⁶	2.28
Plastic Pipe Load Deflection	ASTM D 2412	lbs.	126
Plastic Pipe Flexural Strength	ASTM D 790	lbs.	134
Burst Strength	ASTM D 1180	psi	1300
Physikalische Eigenschaften			
Water Absorption	ASTM D 570	% by wt.	0.5
Dielektrische Eigenschaften			
Arc Resistance	ASTM D 495	sec.	150
Inclined Plane Track Resistance	ASTM D 2303	min.	300

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc. See correlating profile page for sizing and related information.

