

Technisches Datenblatt

Polystone[®] M Reprocessed - ASTM

Typische Eigenschaften

- Economical grade
- Geringer Gleitreibungskoeffizient
- Sehr gute Abrieb- und Verschleißfestigkeit

Typische Industrien

- Fördertechnik & Automation
- Nutz- und Spezialfahrzeuge

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
Dichte	ASTM D792	g / cm ³	0.93 - 0.94
Water Absorption	ASTM D570	%	<0.01
Mechanische Eigenschaften			
Verschleißfestigkeit	Sand-slurry		90
Härte	ASTM D2240	Shore D	63 - 69
Tensile Strength at yield 73°F	ASTM D638	psi	3000
Tensile Modulus	ASTM D638	psi	100000
Reißdehnung	ASTM D638	%	>290
Compressive Strength	ASTM D695	psi	2800
Izod Impact, Notched	ASTM D256	ft-lb/in	No Break
Coefficient of Friction, Dynamic			0.10-0.22
Coefficient of Friction, Static			0.15-0.25
Izod Impact Strength	ASTM D4020		96
Thermische Eigenschaften			
CTE, linear	ASTM D696	in/in/°F	1.1 x 10 ⁻⁴
Melting Point		°F	266 - 275
Maximum Service Temperature, Air		°F	180
Heat Deflection Temperature 264psi	ASTM D648	°F	116
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	116
Flammability, UL94		1/8 inch	HB

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 08/04/2024 • Version: 1.0
 PIM-Version: 32 • PIM-ID: 717948 • PIM-Code: 32-19-10.11.121-11.9-2



	Testverfahren	Einheit	Wert
Elektrische Eigenschaften			
Dielektrizitätszahl	ASTM D150	1MHz	2.3
Durchschlagfestigkeit	ASTM D149		45
Oberflächenwiderstand	ASTM D257	Ω/cm	>10 ¹²
Compliance properties			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

