

Technisches Datenblatt

Polystone[®] P copolymer natur - ASTM

Typische Eigenschaften

- High weldability
- Chemikalienbeständigkeit
- Gute Schlagzähigkeit

Typische Industrien

- Aquafarming
- Reinraumtechnik
- Trink- und Abwassertechnik
- Chemischer Behälter- und Anlagenbau
- Lagerbehälter
- Galvanikanlagen
- Stahlbeizanlagen
- Lüftungsanlagen
- Abluftreinigungsanlagen

| | Testverfahren | Einheit | Wert |
|---|---------------|----------------------------|-----------|
| Allgemeine Eigenschaften | | | |
| Dichte | ASTM D792 | g / cm ³ | 0.91 |
| Water Absorption | ASTM D570 | % | <0.10 |
| Mechanische Eigenschaften | | | |
| Härte | ASTM D2240 | Shore D | 69 |
| Tensile Strength at yield 73°F | ASTM D638 | psi | 3500 |
| Reißdehnung | ASTM D638 | % | ≥300 |
| Flexural Modulus | ASTM D790 | psi | 155000 |
| Compressive Strength | ASTM D695 | psi | 4400 |
| Izod Impact, Notched | ASTM D256 | ft-lb/in | 8.0 |
| Coefficient of Friction, Dynamic | | | 0.25-0.28 |
| Thermische Eigenschaften | | | |
| Coefficient of Linear Thermal Expansion | ASTM D696 | in/in/°F x10 ⁻⁵ | 6 |
| Melting Point | | °F | 323 |
| Maximum Service Temperature, Air | | °F | 180 |
| Heat Deflection Temperature 264psi | ASTM D648 | °F | 210 |
| Flammability, UL94 | | 1/8 inch | HB |

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Release: 20/09/2023

PIM-Version: 43 • PIM-ID: 717966 • PIM-Code: 43-21-9.27.161-5.7.6.7.7.4.6.4.4-2

Page 1 / 2 (Dates in DD/MM/YYYY)



| | Testverfahren | Einheit | Wert |
|----------------------------------|---------------|---------|-------------------|
| Elektrische Eigenschaften | | | |
| Dielektrizitätszahl | ASTM D150 | 1MHz | 2.5 |
| Durchschlagfestigkeit | ASTM D149 | | 45 |
| Oberflächenwiderstand | ASTM D257 | Ω/cm | ≥10 ¹⁴ |
| Compliance properties | | | |
| FDA | | | Yes |
| NSF | | | No |
| USDA | | | Yes |

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

