

Technisches Datenblatt

Sustamid® 6G OL - ASTM

Typische Eigenschaften

- Selbstschmierend
- Verbesserung der "stick-slip" Eigenschaften
- hohe Feuchtigkeitsaufnahme von bis zu 3 % im Normalklima
- Gute Gleiteigenschaften

Typische Industrien

- Maschinen- und Anlagenbau
- Fördertechnik & Automation

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
Dichte	ASTM D792	g / cm ³	1.15
Water Absorption	ASTM D570	%	5.0
Water Absorption 24 hours	ASTM D570	%	1.0
Dissipation Factor	ASTM D150	1MHz	-
Mechanische Eigenschaften			
Härte	ASTM D2240	Shore D	74
Tensile Strength at yield 73°F	ASTM D638	psi	11000
Tensile Modulus	ASTM D638	psi	370000
Reißdehnung	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	14000
Flexural Modulus	ASTM D790	psi	380000
Compressive Strength	ASTM D695	psi	13500
Rockwell Hardness	ASTM D785		85
Rockwell Hardness	ASTM D785	R	115
Shear Strength	ASTM D732	psi	8000
Izod Impact, Notched	ASTM D256	ft-lb/in	1.2
Coefficient of Friction, Dynamic			0.12
Thermische Eigenschaften			
Wärmeleitfähigkeit		in/hr/ft ² /°F	1.7

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Entwurf: 21/09/2023

PIM-Version: 29 • PIM-ID: 717919 • PIM-Code: 29-17-9.10.9.222-5.11-2



	Testverfahren	Einheit	Wert
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	5.0
Melting Point		°F	430
Continuous Service Temperature, Air		°F	210
Flammability, UL94		1/8 inch	HB
Deflection Temperature at 264psi	ASTM D648	°F	200
Deflection Temperature at 66psi	ASTM D648	°F	380
Elektrische Eigenschaften			
Dielektrizitätszahl	ASTM D150	1MHz	3.7
Durchschlagfestigkeit	ASTM D149	V/mil	500
Oberflächenwiderstand	ASTM D257	Ω/cm	>10 ¹³
Compliance properties			
FDA			No
NSF			No
USDA			No

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Entwurf: 21/09/2023

PIM-Version: 29 • PIM-ID: 717919 • PIM-Code: 29-17-9.10.9.222-5.11-2

Page 2 / 2 (Dates in DD/MM/YYYY)

