

Technisches Datenblatt

Sustanat[®] PC MG - ASTM

Typische Eigenschaften

- Biokompatibel

Typische Industrien

- Maschinen- und Anlagenbau
- Elektronik

	Testverfahren	Einheit	Wert
Allgemeine Eigenschaften			
Dichte	ASTM D792	g / cm ³	1.20
Water Absorption 24 hours	ASTM D570	%	0.15
Dissipation Factor	ASTM D150	1MHz	0.006
Water Absorption Saturation	ASTM D570	%	0.35
Mechanische Eigenschaften			
Härte	ASTM D2240	Shore D	80
Tensile Strength at yield 73°F	ASTM D638	psi	10000
Tensile Modulus	ASTM D638	psi	320000
Reißdehnung	ASTM D638	%	75
Flexural Strength	ASTM D790	psi	13000
Flexural Modulus	ASTM D790	psi	340000
Rockwell Hardness	ASTM D785		75
Rockwell Hardness	ASTM D785	R	126
Izod Impact, Notched	ASTM D256	ft-lb/in	10
Thermische Eigenschaften			
Wärmeleitfähigkeit		in/hr/ft ² /°F	1.3
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 ⁻⁵	3.8
Melting Point	ASTM D789	°F	310
Continuous Service Temperature, Air		°F	250
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	280
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	295
Flammability, UL94		1/8 inch	HB
Elektrische Eigenschaften			

Roehling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814
 info.gastonia@roehling.com • www.roehling.com/industrial/rep-us

Print: 27/07/2024 • Entwurf: 21/09/2023

PIM-Version: 25 • PIM-ID: 717960 • PIM-Code: 25-14-16-5.8-2



	Testverfahren	Einheit	Wert
Oberflächenwiderstand	ASTM D257	Ω/cm	$>10^{13}$
Compliance properties			
FDA	ASTM 21EFRI77.1582		Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

