

## Technisches Datenblatt

# Sustason<sup>®</sup> PSU MG - ASTM

### Typische Eigenschaften

- Biokompatibel

### Typische Industrien

- Elektronik
- Back- und Süßwaren
- Getränkeindustrie
- Healthcare
- Lebensmittelindustrie
- Maschinen- und Anlagenbau
- Elektroindustrie

	Testverfahren	Einheit	Wert
<b>Allgemeine Eigenschaften</b>			
Dichte	ASTM D792	g / cm <sup>3</sup>	1.24
Water Absorption 24 hours	ASTM D570	%	0.3
Water Absorption Saturation	ASTM D570	%	0.6
<b>Mechanische Eigenschaften</b>			
Härte	ASTM D2240	Shore D	80
Tensile Strength at yield 73°F	ASTM D638	psi	10200
Tensile Modulus	ASTM D638	psi	360000
Reißdehnung	ASTM D638	%	30
Flexural Strength	ASTM D790	psi	15400
Flexural Modulus	ASTM D790	psi	390000
Rockwell Hardness	ASTM D785		75
Rockwell Hardness	ASTM D785	R	125
Izod Impact, Notched	ASTM D256	ft-lb/in	1.3
<b>Thermische Eigenschaften</b>			
Wärmeleitfähigkeit		in/hr/ft <sup>2</sup> /°F	1.7
Coefficient of Linear Thermal Expansion	ASTM D696	in/in/°F x10 <sup>-5</sup>	3.1
Continuous Service Temperature, Air		°F	300
Deflection Temperature at 1.8Mpa (264psi)	ASTM D648	°F	345
Deflection Temperature at 1.8Mpa (66psi)	ASTM D648	°F	359

#### Röchling Industrial Gastonia, LP

903 Gastonia Technology Parkway • 28034 Dallas/United States (US) • Tel. +1 704 922-7814  
 info.gastonia@roechling.com • www.roechling.com/industrial/rep-us

Print: 27/07/2024 • Entwurf: 21/09/2023

PIM-Version: 29 • PIM-ID: 717964 • PIM-Code: 29-15-16-8.5.6.9.5.5.11-2



	Testverfahren	Einheit	Wert
<b>Elektrische Eigenschaften</b>			
Oberflächenwiderstand	ASTM D257	$\Omega/\text{cm}$	$>10^{13}$
<b>Compliance properties</b>			
FDA			Yes
NSF			No
USDA			Yes

The data stated above are average values ascertained by statistical tests on a regular basis. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

