

## テクニカルデータシート

Durostone<sup>®</sup> UTR 1491 white

## 製品の特徴

- ガラス繊維で強化されたポリエステル樹脂 開閉装置
- 高い機械的強度
- 耐火性
- 煙の発生が極めて少ない

## 製品の用途例

- 再生エネルギー
- 電気
- 電気絶縁
- 発電機およびモーター

	試験法	単位	値
<b>機械的物性</b>			
密度	ASTM D 792	g / cm <sup>3</sup>	1,81
曲げ強度 <sup>⊥</sup>	ASTM D 790	MPa	152
圧縮強度 <sup>⊥</sup>	ASTM D 695	MPa	228
引張強度II	ASTM D 638	MPa	54
<b>熱的物性</b>			
燃焼性	UL 94	/	V0/2,4mm
Temperature index (elec./mech.)	UL 746B	T.I.	130/160
熱伝導率 <sup>⊥</sup>		W / (m * K)	0,27
<b>電気的特性</b>			
Electrical strength (oil/air) <sup>⊥</sup>	ASTM D 149	kV / mm	18/23
Electrical strength (oil) II	ASTM D 149	kV/25mm	47
比較トラッキング指数	UL746A	V	500

⊥ = perpendicular to the lamination II = parallel to the lamination

The data stated above are average values verified on the basis of regular statistical tests and controls. All information in this publication is based on current technical knowledge and experience. Due to the large number of possible influences during processing and application, it does not exempt the user/processor from carrying out their own tests and trials. Responsibility for the evaluation of the end product for the intended use and compliance with the applicable relevant legal requirements lies exclusively with the user/processor as well as the distributor of the respective product/end product. Suggested uses do not constitute an assurance of suitability for the recommended purpose. The information in this publication and our declarations in Connection with this publication do not constitute acceptance of a guaranteed or warranted characteristic. Guarantee declarations require our separate express written declaration in order to be effective. We reserve the right to adapt the product to technical progress and new developments. The products described in this publication are only sold to customers with the appropriate expertise and not to consumers. Please do not hesitate to contact us if you have any questions or if you experience any specific application problems. If the application for which our products are used is subject to an official approval requirement, the user/processor is responsible for obtaining these approvals. Our application recommendations do not exempt the user/processor from the obligation to examine and, if necessary, clarify the possibility of infringements of third-party rights. In all other respects, we refer to our General Terms and Conditions (GTC). These are available at: [www.roechling-industrial.com/gtc](http://www.roechling-industrial.com/gtc)

## Röchling Industrial SE &amp; Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 22/12/2024 • Release: 20/09/2023 • Version: 1.0

PIM-Version: 609 • PIM-ID: 716630 • PIM-Code: 609-36-9.23.12.15-7.6.11.7.4-13

