

テクニカルデータシート

Glastic[®] Glasrod HIR

製品の特徴

- 非常に強く、高温下でも優れた特性を発揮し、電機が容易に取外し可能。
- 優れたコストパフォーマンス
- 寸法安定性

製品の用途例

- 乾式変圧器
- 電気
- 電気絶縁
- 開閉装置
- 変圧器

	試験法	単位	値
一般的物性			
Standard Color			Light Green
機械的物性			
曲げ強度	ASTM D 790	psi	100,000
引張強度	ASTM D 638	psi	90,000
引張弾性率	ASTM D 638	psi X 10 ⁶	3
IZOD Impact Strength (notched)	ASTM D 256	ft. lb./in.	60
In-Plane Shear Strength	ASTM D 3914	psi	3,500
Compressive Strength - Axial	ASTM D 695	psi	60,000
Compressive Strength - Transverse	ASTM D 695	psi	16,000
熱的物性			
Coefficient of Thermal Expansion	ASTM D 696	(in./in.°C) x 10-5	0.6
熱伝導率	ASTM C 177		2
機械的特性			
比重	ASTM D 792		1.9
Water Absorption	ASTM D 570	%	0.1
電気的特性			
Arc Resistance	ASTM D 495	sec.	150
Permittivity, 60 Hz	ASTM D 150		5
Insulation Resistance	ASTM D 257	$\Omega \times 10^{12}$	100



	試験法	単位	値
Electrical Strength - Axial in Oil		kV	80

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Röchling Glastic Composites products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage. Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc. See correlating profile page for sizing and related information.

