

## テクニカルデータシート

LubX<sup>®</sup> CV natural

## 製品の特徴

- 高負荷時でも優れた摺動性を発揮
- 優れた乾燥性
- FDA規格適合
- 良好な機械加工性
- GMP 2023/2006 ECに準拠

## 製品の用途例

- 機械工学
- コンベヤー
- 食品
- 肉、魚、鶏肉加工
- 製パンおよび製菓
- 飲料

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	0,94
吸水率	DIN EN ISO 62	%	<0,01
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
無毒性			+
<b>機械的物性</b>			
引張降伏応力	DIN EN ISO 527	MPa	19
引張破壊呼び歪	DIN EN ISO 527	%	>250
引張弾性率	DIN EN ISO 527	MPa	800
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m <sup>2</sup>	no break
シヨア硬度	DIN EN ISO 868	scale D	60
スライド性: 相手材 PET (0,5 m/s - 0,5 MPa)	REP – Tribology – Test		0,13
<b>熱的物性</b>			
融点	ISO 11357-3	°C	133 – 135
線膨張係数	DIN 53752	10 <sup>-6</sup> / K	150 - 230 (*)
使用温度 (長期)	平均値	°C	-150 ... 80 (*)
使用温度 (短期、最大)	平均値	°C	130 (*)
<b>電気的物性</b>			
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	>10 <sup>15</sup>
表面固有抵抗	DIN EN 62631-3-2	Ω	>10 <sup>14</sup>

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (\*) literature values



**Röchling Industrial SE & Co. KG**

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 13/03/2025 • Release: 21/02/2025 • Version: 2.0

PIM-Version: 585 • PIM-ID: 718591 • PIM-Code: 585-42-16.18.15.70.15-5.11.5.5.5.6-4

Page 2 / 2 (Dates in DD/MM/YYYY)

