

テクニカルデータシート

Polystone[®] M Slide grey pressed

製品の特徴

- 低摩擦係数
- 静音性
- 自己潤滑性
- UV耐性
- 非常に優れた耐摩耗性

製品の用途例

- コンベヤー
- 肉、魚、鶏肉加工
- 飲料
- 機械工学
- 食品

	試験法	単位	値
一般的物性			
密度	DIN EN ISO 1183-1	g / cm ³	>0,95
吸水率	DIN EN ISO 62	%	<0,01
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
分子量	-	10 ⁶ g/mol	~ 9
機械的物性			
引張降伏応力	DIN EN ISO 527	MPa	>20
引張破壊呼び歪	DIN EN ISO 527	%	>50
引張弾性率	DIN EN ISO 527	MPa	>600
ノッチ付き衝撃耐性	DIN EN ISO 11542	kJ / m ²	>110
シヨア硬度	DIN EN ISO 868	scale D	>60
熱的物性			
融点	ISO 11357-3	°C	130 ... 135
熱伝導率	DIN 52612-1	W / (m * K)	0,40
熱容量	DIN 52612	kJ / (kg * K)	1,90
線膨張係数	DIN 53752	10 ⁻⁶ / K	150 ... 230
使用温度 (長期)	平均値	°C	-250 ... 80
使用温度 (短期、最大)	平均値	°C	130
ビカットB軟化温度	DIN EN ISO 306, Vicat B	°C	79
電氣的物性			

	試験法	単位	値
誘電率	IEC 60250		2,3
誘電正接 (10 ⁶ Hz)	IEC 60250		0,0001
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
表面固有抵抗	DIN EN 62631-3-2	Ω	>10 ¹⁴
比較トラッキング指数	IEC 60112		600
絶縁破壊電圧	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0
info@roechling-plastics.com • www.roechling.com/industrial/haren

Print: 21/11/2024 • Release: 20/09/2023 • Version: 2.0

PIM-Version: 589 • PIM-ID: 591101 • PIM-Code: 589-32-12.13.10.15.126-11.5.6.5.5-5

Page 2 / 2 (Dates in DD/MM/YYYY)

