

## テクニカルデータシート

Polystone<sup>®</sup> P (Homopolymer) white pressed

## 製品の特徴

- 高剛性
- 良好な溶接性
- 耐腐食性

## 製品の用途例

- 化学産業
- クリーンルーム
- 電解設備
- 排気浄化設備
- ケミカルタンク
- 換気設備

	試験法	単位	値
<b>一般的物性</b>			
密度	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,90
吸水率	DIN EN ISO 62	%	<0,1
燃焼性 (厚み 3 mm / 6 mm)	UL 94		HB
<b>機械的物性</b>			
引張降伏応力	DIN EN ISO 527	MPa	>30
引張破壊呼び歪	DIN EN ISO 527	%	>50
引張弾性率	DIN EN ISO 527	MPa	>1500
ノッチ付き衝撃耐性	DIN EN ISO 179	kJ / m <sup>2</sup>	>4
ショア硬度	DIN EN ISO 868	scale D	>70
<b>熱的物性</b>			
融点	ISO 11357-3	°C	162 ... 167
熱伝導率	DIN 52612-1	W / (m * K)	0,20
熱容量	DIN 52612	kJ / (kg * K)	1,70
線膨張係数	DIN 53752	10 <sup>-6</sup> / K	120 ... 190
使用温度 (長期)	平均値	°C	0 ... 100
使用温度 (短期、最大)	平均値	°C	150
ピカットB軟化温度	DIN EN ISO 306, Vicat B	°C	90
<b>電気的物性</b>			
誘電率	IEC 60250		2,4

	試験法	単位	値
誘電正接 (10 <sup>6</sup> Hz)	IEC 60250		0,00019
体積固有抵抗	DIN EN 62631-3-1	Ω * cm	>10 <sup>14</sup>
表面固有抵抗	DIN EN 62631-3-2	Ω	>10 <sup>14</sup>
絶縁破壊電圧	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.



### Röchling Industrial SE & Co. KG

Röchlingstr. 1 • 49733 Haren (Ems)/Germany (DE) • Tel. +49 5934 701-0  
[info@roechling-plastics.com](mailto:info@roechling-plastics.com) • [www.roechling.com/industrial/haren](http://www.roechling.com/industrial/haren)

Print: 02/11/2024 • Release: 06/10/2023 • Version: 3.0  
 PIM-Version: 580 • PIM-ID: 746400 • PIM-Code: 580-26-11.16.21-7.7.4.4.7.4-5

